

# SBS RP 8361

## Styrene-butadiene-styrene block copolymer

Radial styrene-butadiene thermoplastic elastomer SBS RP 8361 is essentially a product of styrene and butadiene block polymerization in hydrocarbon solution in the presence of alkyllithium catalyst. SBS RP 8361 is dusted with calcium stearate, zinc stearate or amorphous silica. It is containing a no staining stabilizer.

**Appearance:** crumbs or powder white to light-beige color; weight — 14 kg or 800–1000 kg

**Package:** pallets or soft bag-container (big bag)

**Shelf life:** 1 year since the date of manufacture

**Storage conditions:** not higher than 40 °C, in place protected from direct sunlight and atmospheric precipitation

Parameters	SBS R 7382	Test method
Volatile matter content, wt %	≤0,5	ASTM D 5668
Ash content, wt %:		
a) calcium stearate or zinc stearate	≤0,3	ASTM D 5667
b) silica	≤1,2	
Content of bound styrene, wt %	28,5–31,5	method of supplier
Melt flow index, 190 °C/ 5 kg, g/10 min	8,0–14,0	method of supplier
Tensile strength, MPa	3,5	ASTM D 412
Tensile stress at 300 % elongation, MPa	1,0	ASTM D 412
Ultimate elongation, %	600	ASTM D 412
Hardness, Shore A	47–59	ASTM D 2240
Paraffin-naphthenic oil content, %	29–33	

Technical support service: [techservice@sibur.ru](mailto:techservice@sibur.ru)

Issue: **01-April-2020**

### MOSCOW

16/1 Krzhizhanovskogo St., Moscow,  
117218  
Phone: +7 (495) 777-55-00; +7 (495)  
780-55-00  
E-mail: [info@sibur.ru](mailto:info@sibur.ru)

### VIENNA

SIBUR International Gesellschaft m.b.H.  
Prinz Eugen-Straße 8-10 1040 Vienna, Austria  
tel.: +43 1 370 8000  
e-mail: [info@sibur-int.com](mailto:info@sibur-int.com)  
[www.sibur-int.com](http://www.sibur-int.com)

### ISTANBUL

SIBUR International Trading (Istanbul)  
Business Park, B1 Blok, Kat.9, No.318,  
Yeşilköy, Bakırköy, Istanbul, Turkey  
tel.: +90 (212) 465 2321  
e-mail: [info@sibur-int.com](mailto:info@sibur-int.com)  
[www.sibur-int.com](http://www.sibur-int.com)

### SHANGHAI

SIBUR International Trading (Shanghai) Co., Ltd  
Rm.62T70, SWFC Century Ave.100 Pudong New  
Area, Shanghai  
tel: +86 (021) 2206 5066  
e-mail: [infoChina@sibur-int.com](mailto:infoChina@sibur-int.com)  
[www.sibur-int.cn](http://www.sibur-int.cn)