

PRODUCT DESCRIPTION

SIBEX® PP H031 BF/3 is a polypropylene homopolymer with standard molecular weight distribution. The product is characterized by medium melt flow rate, an optimal stabilization package without metal stearates and balanced physical and mechanical properties.

TYPICAL APPLICATIONS

SIBEX® PP H031 BF/3 is recommended for biaxially oriented polypropylene film extrusion, especially for metallized BOPP. It complies with EU Food Contact Regulations.

Physical Properties	Method	Typical values*
Rheology		
Melt Flow Rate (230 °C/2.16 kg)	ISO 1133	3.0 g/10 min
Mechanical		
Tensile stress at yield (50 mm/min)	ISO 527	32 MPa
Elongation at yield (50 mm/min)	ISO 527	11 %
Flexural modulus (50 mm/min)	ISO 178	1200 MPa
Notched Izod impact strength (23 °C)	ISO 180	3.0 kJ/m ²
Rockwell hardness	ISO 2039-2	109
Thermal		
Vicat softening temperature (10 N)	ISO 306	162 °C
Heat deflection temperature (0.45 MPa)	ISO 75-2	91 °C

*Typical values; not for specification.

REACH Statement

Polymers are exempt of REACH registration. However, their raw materials which mean monomers and relevant additives have been registered.

PJSC «Sibur Holding» (and its subsidiaries) is committed to fully respect REACH legislation and to use only REACH compliant raw materials.

Safety

See MSDS

Contact

PJSC «Sibur Holding»

Basic Polymers Division
3-16, Krzhizhanovskogo St.
117997, Moscow, Russian Federation
Tel.: ++7 495 7775500
E-mail: servicedbp@sibur.ru

European Sales Office

Sibur International GmbH
Prinz Eugen Straße 8-10
1040, Vienna, Austria
Tel.: ++43 1 370 8000
E-mail: polyolefins@sibur-int.com

Turkey Sales Office

SIBUR Istanbul Uluslararası Tic. Ltd. Şti.
Ferko Signature Levent
Esentepe, Büyükdere Cd. No:175, 4.Kat / A25
34394 Şişli, Istanbul, Turkey
Tel: ++90 212 919 0035
E-mail: polyolefins@sibur-int.com

Chinese Sales Office

SIBUR International Trading (Shanghai)Co., Ltd
Rm.62T70, SWFC, Century Ave.100 Pudong New
Area, 200120, Shanghai, China
Tel: ++86 021 2206 5066 ext 215
E-mail: serviceCN@sibur-int.com

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications. To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information. PJSC «Sibur Holding» (and its subsidiaries) makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of any PJSC «Sibur Holding» (and its subsidiaries) product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.